



ELASTOTET S.A.

SEALING & ADHESIVE MATERIALS

Silicone, Acrylic & Polyurethane Sealants

ELASTOTAN-S

DESCRIPTION

ELASTOTAN-S is a one component moisture-cured sealant that cures at room temperature to produce a flexible low modulus elastomeric seal.

CHARACTERISTICS

- ELASTOTAN-S DOES NOT CAUSE STAINS ON NATURAL STONES
- It will adhere without primer to most common building substrates.
- Once cured it has a movement capability of $\pm 25\%$ over a wide range of temperatures.

ELASTOTAN-S sealant combines the advantages of a low modulus elastomeric sealant (minimum strain on joint surfaces) with primerless adhesion on most construction materials including porous substrates. Its curing characteristics enable easy application and tooling of the product. **Mechanical properties and adhesion are not affected by prolonged exposure to sunlight, rain, snow or ozone.**

ELASTOTAN-S sealant can be used on glass, coated glass, vitreous surfaces, metal, painted or unpainted wood, PVC, polycarbonates, polymethacrylates, ABS, concrete, granite, marble etc.

TYPICAL USES

ELASTOTAN-S is recommended for sealing of joints of every kind between similar as well as dissimilar substrates in buildings and civil engineer constructions, as : Concrete joints (expansion-contraction, interruption joints etc), window and door fittings (adhesion to concrete, plaster, glass, aluminium, wood, marble, stone, ceramics, asbestos cement, plastic), pipe fittings (metal or PVC), fittings of PVC membranes (insulating linings of roofs etc.).

ELASTOTAN-S IS ESPECIALLY SUITABLE FOR APPLICATIONS ON BUILDING FACADES OF NATURAL STONES, LIKE MARBLE, GRANITE AND CONCRETE.

TYPICAL PROPERTIES

Specific gravity, approx.: 1,36

Sag, Slump (ISO 7390): No sag

Skin over time : 20-30 min

Cure time

approx.: 2-3 mm/1 st day

7-9 mm/7 days

Application temperature range: +5 to +40 °C

Service temperature range: -50 to +120 °C

Joint movement capability: $\pm 25\%$

Hardness : approx. 22

Elastic recovery : approx. 95%

Mechanical properties on slabs (DIN 53504)

- Tensile at 100% elongation: approx. 0,62 MPa
- Tensile strength: approx. 1,1 MPa
- Elongation at break: approx. 400%

APPLICATION PROCEDURE

Joint preparation: The joint faces to be bonded must be clean, dry and free from dust, oil, grease, old sealant and any traces of contaminant that may affect adhesion. Surfaces should be degreased with solvent using a clean cloth.

Priming: ELASTOTAN-S sealant does not normally require primer on most common substrates used in buildings. In cases of expansion joints with porous substrates (concrete), a PRIMER VL is recommended. The sealant is applied after the primer has completely dried (2-3 hrs to 24 hrs depending on temperature and moisture. When the primer is dry is tack free).

Joint dimensions: The movement capability of sealant as well as local regulations must be considered. Joint width should be twice the depth when the width is bigger than 20mm and equal to the depth when the width is smaller than 20mm. The width of the joints must not be less than 5 and bigger than 50mm.

Sealant application: For good performance it is essential that the sealant be only bonded to the two facing sides of the joint. To achieve this install a backup material (closed cell polyethylene or open cell polyurethane foam). Apply the sealant in a continuous operation making sure all air pockets or voids are eliminated. Tool the sealant with light pressure to spread the material against the joint surfaces.

This operation should be made with a dry spatula before skin formation occurs.

Excess uncured sealant should be wiped and cleaned with a commercial solvent such as white spirit, cured sealant can only be removed by abrasion.

PACKAGING

In plastic cartridges of 0,28 Lt content and sausages 0,6 Lt .

COLOURS

White, Grey, Black. Other colours upon request.

LIMITS OF USE

ELASTOTAN-S sealant is not recommended for use on materials where migration of constituents can take place, e.g. certain rubbers. It must not be used for jointing aquariums or swimming pools. It cannot be painted.

STORAGE AND SHELF LIFE

ELASTOTAN-S sealant has a shelf life of 12 months from its date of manufacture (the manufacture date is shown on the packaging) under normal storage conditions.

Warning to users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELASTOTET GUARANTEES THAT ITS PRODUCTS COMPLY WITH ITS SALES SPECIFICATIONS. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELASTOTET is at their disposal to supply any additional information.