



**ELASTOTET S.A.**

**SEALING & ADHESIVE MATERIALS**

**Silicone, Acrylic & Polyurethane Sealants**

---

# PARQUET FLOORING ACRYSEAL

One component flexible sealant and gap filler based on acrylic resins in wood colours for filling joints in floors, doors, windows and furniture.

## PHYSICAL AND TECHNICAL PROPERTIES

**Colours:** Oak, Beech, Cherry, Maple, Mahogany, Nut. It can be painted after curing.

**Density :** 1,5 g/cm<sup>3</sup>

**Surface membrane formation time:** 10-15 min

**Curing time for 5 mm sealing depth:** 4-5 days

(depending on environmental condition)

**Elongation at break (DIN 53504) :** ca. 500%

**Modulus 100% (DIN 53504) :** ca. 0,15 N/mm<sup>2</sup>

**Hardness SHORE A (DIN 53505) (3S) :** 20±3

**Thixotropy:** Suitable for sealing vertical joints (it does not sag).

After application, the water, which the sealant contains, evaporates into open air. After the evaporation, the sealant turns to a cohesive plastoelastic mass which adheres to the sides of the joint.

## APPLICATION FIELDS

It is especially suitable for joints around timber, laminates and melamine coated board in flooring and furniture applications. It also suitable for joints around wooden, aluminium or PVC doors and windows. **PARQUET FLOORING ACRYSEAL** is suitable for joints without large working width change (up to 8%).

It is not suitable for sealing of joints permanently immersed in water (water tanks etc.).

## APPLICATION INSTRUCTIONS

The environmental temperature must not be below 10°C during application.

Days of rain possibility must be avoided, because during the first hours after application the material must not be exposed to rain.

**Preparation:** The substratum must be free of dust and loose particles. Cleaning by means of a wire-brush and blowing with compressed air, if available, is recommended.

To avoid the soiling of the joint edges we put self-sticking paper tape (masking tape) along the edges. This tape must be removed immediately after sealing (before curing of the sealant).

**Sealing:** We put the cartridge/sausage into the suitable gun, cut the nozzle slantwise to form an opening proportional to the joint width and apply the sealant into the joint. The smoothing of the surface of the sealant, if needed, must be done with a spatula immediately after application, because after about 5 minutes the surface membrane formation begins. We, also, remove the masking tape before membrane formation.

**Cleaning of tools and hands:** Unless dry, the sealant is easily removed with water (preferably hot). If dry, it is removed mechanically (by scraping). The product is normally harmless and it doesnot need special precautions during application.

**Curing:** It begins immediately after application (contact with air) and is completed after one month (approximately), when the sealant obtains its final properties.

**Shelf Life:** 12 months in original packing between 5 and 25 °C.

**Packing:** 280 ml cartridge.

#### **Warning to users**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELASTOTET GUARANTEES THAT ITS PRODUCTS COMPLY WITH ITS SALES SPECIFICATIONS. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELASTOTET is at their disposal to supply any additional information.