



VIMACRET®

Pre-mixed resin improved cement mortar

Properties

VIMACRET is a pre-mixed resin improved cement mortar in powder form. By adding only water you will get a mortar

- with perfect bonding to the substrate
- without cracks, waterproofing and with high strengths
- without substances that could corrode the iron

Applications

- Suitable for internal and external use on dry or wet substrate
- Repair of concrete elements (filling cavities, covering reinforcements)
- Restore imperfections, cracks and local coating reconstructions
- Very strong and waterproofing cement mortars
- Suitable for use in potable water tanks¹
- Fastening and anchoring machines
- Construction of skirting boards – pipes in basements and tanks before applying **WATERBLOCK**.

Technical Data²

Bulk density of dry mortar (ELOT EN 1097-03)	1,69 kg/l
Mixing water (percentage in dry mortar)	16%
Cohesion (ELOT EN 1015-04)	1,6 cm
Bulk density of fresh mortar (ELOT EN 1015-06)	1,74 kg/l
Efficiency	0,68 kg/l
Mechanical strengths (ELOT EN 1015-11)	
Compressive strength:	13,2 Mpa
Flexural strength:	3,7 Mpa

¹ Certificate of conformity for use in potable water tanks, issued by the Laboratory of Analytical Chemistry, Aristotle University of Thessaloniki

² Test Report, issued by the accredited Laboratories CERECO S.A.

VIMATEC - N. VIDALIS S.A.
CONSTRUCTION CHEMICALS TECHNOLOGIES



Head: 1-3, Makedonias str, GR-546 41 Thessaloniki GREECE
Tel: +30-2310 858561, +30-2310 843093 Fax: +30-2310843566
Branch: 8, Narkissou str, GR-136 72 Acharnes Attiki GREECE
Tel: +30-210 2828435 Fax: +30-210 2829434
e-mail: info@vimatec.gr
> www.vimatec.gr <



Substrate Preparation

The substrate must be sound, clear of dust, rotten materials and loosen parts. Oils and grease can be removed with **VIMACLEAN**.

Wet the substrate well before using **VIMACRET**, avoiding any excess water.

How to use

VIMACRET is slowly added into water and stirred until the mixture is uniform and has the required workability.

Indicatively, use around 4,0 – 4,5 kg of water per bag of **VIMACRET** (25 kg).

Fresh mortar pot life is about 45-50 minutes.

Do not add more water in order to soften the mortar if hardening has already started.

Consumption

For a 1 cm layer and a surface of 1m² use around 15 kg of **VIMACRET**.

For making a 5-7 cm haunch pipe you will need around 3-4 kg/m.

Caution

In high temperatures or windy conditions fresh **VIMACRET** must be wetted in order to be protected from quick dehydration.

Cracks caused by setting shrinkage can be eliminated by mixing the polypropylene fibres **FIBERPLUS** into the fresh **VIMACRET** using a ratio of 15-20 g / 25 kg bag.

Adding other materials except for water into **VIMACRET** will cause alteration of **VIMACRET**'s properties.

Cleaning of tools

Tools must be cleaned with water immediately after use, before the mixture dries.

Storing

VIMACRET can be stored in a dry environment and in sealed bags for at least 12 months

Packaging

In 25 kg bag, available in grey colour

Protection

Contains cement so that it is considered as irritant due to alkali reaction with water

VIMATEC - N. VIDALIS S.A.
CONSTRUCTION CHEMICALS TECHNOLOGIES



Head: 1-3, Makedonias str, GR-546 41 Thessaloniki GREECE
Tel: +30-2310 858561, +30-2310 843093 Fax: +30-2310843566
Branch: 8, Narkissou str, GR-136 72 Acharnes Attiki GREECE
Tel: +30-210 2828435 Fax: +30-210 2829434
e-mail: info@vimatec.gr
> www.vimatec.gr <