



VIMACRET®-RAPID

*Fast setting, resin improved,
reinforced cement mortar*

Properties

VIMACRET RAPID is an ideal pre-mixed, repairing, and fast setting (30-35 minutes) cement mortar, which provides to the applicator the advantage of constant working. The other advantages of **VIMACRET RAPID** are:

- perfect bonding to the substrate
- eliminates shrinkage setting
- high mechanical strengths

Applications

It is appropriate for every cement mortar application, where parallel fast setting of the material is demanded:

- Fixing, anchoring, e.g. metal constructions, machinery
- Preparation of the substrate before the application of the brushable sealing slurry **WATERBLOCK** (sealing of cavities and other imperfections of the concrete's surface, construction of sealing perimetric gutters) and continuance of the waterproofing without waiting time.

Technical Data*

Bulk density of dry mortar (ELOT EN 1097-03)	1,47 kg/l
Mixing water (percentage in dry mortar)	18%
Cohesion (ELOT EN 1015-04)	1,6 cm
Bulk density of fresh mortar (ELOT EN 1015-06)	1,99 kg/l
Efficiency	0,61 kg/l
Mechanical strengths (ELOT EN 1015-11)	
Compressive strength:	18,1 Mpa
Flexural strength:	5,1 Mpa

* Tests Report, issued by the accredited Laboratories CERECO S.A.



VIMATEC - N. VIDALIS S.A.
CONSTRUCTION CHEMICALS TECHNOLOGIES

Head: 1-3, Makedonias str, GR-546 41 Thessaloniki GREECE
Tel: +30-2310 858561, +30-2310 843093 Fax: +30-2310843566
Branch: 8, Narkissou str, GR-136 72 Acharnes Attiki GREECE
Tel: +30-210 2828435 Fax: +30-210 2829434
e-mail: info@vimatec.gr
> www.vimatec.gr <